



## PEGAMAT® RL ISOLE

# Low tension renovation and stain blocking paint

- Good covering power
- Low odour
- Non yellowing
- Low tension film
- Unsaponifiable

# PEGAMAT® RL ISOLE

## DESCRIPTION

Deodorised low tension solvent-based insulating or blocking paint based on plastified acrylic resins.

## RECOMMENDED USE

Low tension renovation paint for interior walls and ceilings.

## TECHNICAL DATA

Density (g/cm³):	1.33 - 1.37 g/cm³
Gloss Level:	Matt
Gloss level at 60°:	Matt: < 2%
Solids Content in weight:	64 - 66%
Solids content in volume:	38 - 40%

## DRY TIMES BY 20° C/RH 50%

Touch dry:	3 h
Dry to recoat:	Wet in wet or after 4 h
Fully cured:	1 day

## RECOMMENDED WET FILM THICKNESS

100 µm

## RECOMMENDED DRY FILM THICKNESS

40 µm

## THEORETICAL CONSUMPTION

9 - 12 m²/l per coat

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc. Substrates should be sufficiently dry and stable. Apply 1 or 2 coats according to the condition of the substrate; if necessary, the second coat can be applied wet in wet. Do not apply on Elastofill; when using Pegaflex, it must first be insulated with Porisol.

Old cleaned layers in good condition and light porous substrates may be recoated directly with Pegamat RL Isole.

Very porous substrates are to be impregnated first with Pegafix.

Persistent stains are to be treated with Pegaprim® Isofix.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

## APPLICATION & THINNING: BRUSH

Dilute with 3-5% Thinner RL or White spirit if necessary.

## APPLICATION & THINNING: ROLLER

Dilute with 3-5% Thinner RL or White spirit if necessary.

## APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 011 - 015 / Pressure: 180 bars.

Dilute max. 5% with Thinner RL or White spirit if necessary.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Possible.

## CLEANING OF EQUIPMENT / SPILLS

White spirit.

## REMARKS

White spirit increases the odour and makes its use impossible on polystyrene foam.

Pegamat RL Isole is a reversible paint system, this means that it dissolves in its own solvent. Therefore, dried spots of Pegamat RL Isole can be removed with Thinner RL or white spirit. Do not tint with universal pigments or on the tinting machine.

## SAFETY DATA

VOC level:	455 g/l
VOC readymix:	485 g/l
VOC category:	A/i
VOC limit:	500 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 07/02/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)