



PEGAMAT® RL ISOLE

Low tension renovation and stain blocking paint

- Good covering power
- Low odour
- Non yellowing
- Low tension film
- Unsaponifiable

PEGAMAT® RL ISOLE

POPIS PRODUKTU (DLHÝ)

Deodorised low tension solvent-based insulating or blocking paint based on plastified acrylic resins.

ODPORÚČANÉ POUŽITIE

Low tension renovation paint for interior walls and ceilings.

TECHNICAL_DATA

Hustota (g/cm ³):	1.33 - 1.37 g/cm ³
Úroveň lesku:	Matt
Úroveň lesku pri 60°:	Matt: < 2%
Obsah pevných látok v hmotnosti:	64 - 66%
Obsah pevných látok v objeme:	38 - 40%

DRY_TIMES_BY_20

Na dotyk suché:	3 h
Suchý na opätovné natieranie:	Wet in wet or after 4 h
Úplne vytvrdnuté:	1 day

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

40 µm

TEORETICKÁ SPOTREBA

9 - 12 m²/l per coat

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc. Substrates should be sufficiently dry and stable. Apply 1 or 2 coats according to the condition of the substrate; if necessary, the second coat can be applied wet in wet. Do not apply on Elastofill; when using Pegaflex, it must first be insulated with Porisol.

Old cleaned layers in good condition and light porous substrates may be recoated directly with Pegamat RL Isole.

Very porous substrates are to be impregnated first with Pegafix.

Persistent stains are to be treated with Pegaprim® Isofix.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

Dilute with 3-5% Thinner RL or White spirit if necessary.

APLIKÁCIA A RIEDENIE: VALEC

Dilute with 3-5% Thinner RL or White spirit if necessary.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 011 - 015 / Pressure: 180 bars.

Dilute max. 5% with Thinner RL or White spirit if necessary.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Possible.

ČISTENIE ZARIADENIA / POSTRIEKANIE

White spirit.

POZNÁMKY

White spirit increases the odour and makes its use impossible on polystyrene foam.

Pegamat RL Isole is a reversible paint system, this means that it dissolves in its own solvent. Therefore, dried spots of Pegamat RL Isole can be removed with Thinner RL or white spirit. Do not tint with universal pigments or on the tinting machine.

DATA_SAFETY_DATA

Úroveň VOC:	455 g/l
VOC readymix:	485 g/l
Kategória VOC:	A/i
Limit VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu