



Quality Paints since 1845
MATHYS®



PEGAMAT® RL ISOLE

Low tension renovation and stain blocking paint

- Good covering power
- Low odour
- Non yellowing
- Low tension film
- Unsaponifiable

PEGAMAT® RL ISOLE

BESKRIVNING

Deodorised low tension solvent-based insulating or blocking paint based on plastified acrylic resins.

REKOMMENDERAD ANVÄNDNING

Low tension renovation paint for interior walls and ceilings.

TEKNISK DATA

Densitet:	1.33 - 1.37 g/cm ³
Glansnivå:	Matt
Glansnivå vid 60°:	Matt: < 2%
Torrsubstansvikt:	64 - 66%
Torrsubstansvolym:	38 - 40%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	3 h
Övermålningsbar:	Wet in wet or after 4 h
Fullt härdad:	1 day

REKOMMENDERAD VÅTFILMSTJOCKLEK

100 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

40 µm

TEORETISK FÖRBRUKNING

9 - 12 m²/l per coat

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc. Substrates should be sufficiently dry and stable. Apply 1 or 2 coats according to the condition of the substrate; if necessary, the second coat can be applied wet in wet. Do not apply on Elastofill; when using Pegaflex, it must first be insulated with Porisol.

Old cleaned layers in good condition and light porous substrates may be recoated directly with Pegamat RL Isole.

Very porous substrates are to be impregnated first with Pegafix.

Persistent stains are to be treated with Pegaprim® Isofix.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

APPLICERING OCH SPÄDNING: PENSEL

Dilute with 3-5% Thinner RL or White spirit if necessary.

APPLICERING OCH SPÄDNING: ROLLER

Dilute with 3-5% Thinner RL or White spirit if necessary.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Nozzle: 011 - 015 / Pressure: 180 bars.

Dilute max. 5% with Thinner RL or White spirit if necessary.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Possible.

RENGÖRING AV UTRUSTNING/SPILL

White spirit.

ANMÄRKNINGAR

White spirit increases the odour and makes its use impossible on polystyrene foam.

Pegamat RL Isole is a reversible paint system, this means that it dissolves in its own solvent. Therefore, dried spots of Pegamat RL Isole can be removed with Thinner RL or white spirit. Do not tint with universal pigments or on the tinting machine.

SÄKERHETSDATA

VOC-nivå:	455 g/l
VOC färdigmix:	485 g/l
VOC-kategori:	A/i
VOC-gräns:	500 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskadorna. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu