



PEGAPRIM® XPRESS

Fast drying universal and stain block primer

- Quick drying
- Flexible/insulating
- Good filling and hiding power
- Closed good adhering paint film
- Recoatable with most water and solvent borne decorative paints

PEGAPRIM® XPRESS

BESKRIVELSE

Insulating and fast drying universal adhesion primer based on water borne acrylic resins.

ANBEFALET BRUG

For inside and outside.

Adhesion on metal (steel, zinc, aluminium, galvanised steel) and on smooth hard surfaces (PVC, polyester, Formica). Closes porous substrates (masonry, plaster rendering, concrete, wood, fibreboards).

Insulates spots (tar, soot, graffiti, humidity); in difficult circumstances use Pegaprim Isofix.

TEKNISK DATA

Tæthed:	± 1,26
Glansgrad:	Satin
Glansgrad ved 60°:	Satin gloss: ± 15%
Faststofindhold i vægt:	± 52 %
Tørstofindhold i volumen:	± 39 %

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	30 minutes
Genbehandlingstør:	1 hour
Fuldt hærdet:	2 days

ANBEFALET VÅDFILMTYKKELSE

100 µm

ANBEFALET TØRFILMTYKKELSE

40 µm

TEORETISK FORBRUG

± 10 m²/l per coat

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application

FORBEHANDLING AF OVERFLADEN

The surface should be clean, dry and stable.

Where necessary, degrease.

Contamination has to be removed as thoroughly as possible.

Reinforce the wood structure if necessary (e.g. after burning off of new wood on the outside) by impregnating with Adex.

Wood knots have to be insulated beforehand with Pegapim Isofix.

Old intact lacquer paint coats should be roughened up slightly in order to assure an optimal adhesion.

In case of doubt, realise an adhesion test.

When applied as spot insulator, a longer drying time should be respected before recoating.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANVENDELSESBETINGELSER

> 5°C, < 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL

Apply preferably undiluted.

PÅFØRING OG FORTYNDING: RULLE

Apply preferably undiluted.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Nozzle: 0,011 - 0,013 inch / Pressure: 200 bars.

If necessary, dilute with water.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

Dilute with a few % volume of water.

RENGØRING AF Udstyr/SPILD

Water.

SIKKERHEDSDATA

VOC-niveau:	40 g/l
VOC-færdigblanding:	40 g/l
VOC-kategori:	A/g
VOC-grænse:	30 g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 07/02/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu