

Quality Paints since 1845
MATHYS[®]



PLASTI-PARKET

Parquet floor protection

- Simple to use
- Air-drying
- Excellent resistance against abrasion
- Makes maintenance easier
- Suitable for spot repairs



PLASTI-PARKET

BESKRIVELSE

Solvent-based varnish based on a modified polyurethane alkyd binder.

ANBEFALET BRUG

Treatment and protection of parquet floors and wooden staircases.

TEKNISK DATA

Tæthed:	0,90 - 0,92
Glansgrad:	Satin
Glansgrad ved 60°:	Semi gloss: ± 15%
Faststofindhold i vægt:	52 - 54 %
Tørstofindhold i volumen:	43 - 45 %

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	1,5 hours
Genbehandlingstør:	24 hours
Fuldt hærdet:	1 week

ANBEFALET VÅDFILMYKKELSE

100 µm

ANBEFALET TØRFILMYKKELSE

40 µm

TEORETISK FORBRUG

± 10 m²/l per coat

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

New parquet floors or parquet floors rub down until bare wood: dedust thoroughly, impregnate with FassiForce and let dry for minimum one night. After this, rub down lightly. Remark: replace FassiForce with diluted Duritane Gloss if the wood is colored too strongly. Old parquet floors already treated with wax: first remove the wax layer thoroughly (scrape). Use cleaning cloths soaked with white spirit. After this, apply one coat FassiForce. The FassiForce layer should be completely dry the next day. If this is not the case, it is an indication that the old wax layer was not removed enough. Clean the floor again as described above.

Remark: use sufficient cleaning cloths to remove the wax layer in order to avoid that the removed wax is applied on other parts of the floor.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANVENDELSESBETINGELSER

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL

If necessary dilute with maximum 5% volume white spirit or Thinner 22.

PÅFØRING OG FORTYNDING: RULLE

If necessary dilute with maximum 5% volume white spirit or Thinner 22. Use a fine roller.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Not recommended.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

Not recommended.

RENGØRING AF UDSKYR/SPILD

White spirit or Thinner 22.

BEMÆRKNINGER

Mix Plasti-Parket during application in order to make sure that the product will stay homogeneous.

Apply minimum 2 coats of Plasti-Parket.

SIKKERHEDSDATA

VOC-niveau:	445 g/l
VOC-færdigblanding:	466 g/l
VOC-kategori:	A/i
VOC-grænse:	500 g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 07/06/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu