



## PLASTI-PARKET

# Parquet floor protection

- Simple to use
- Air-drying
- Excellent resistance against abrasion
- Makes maintenance easier
- Suitable for spot repairs



# PLASTI-PARKET

## DESCRIPTION

Solvent-based varnish based on a modified polyurethane alkyd binder.

## RECOMMENDED USE

Treatment and protection of parquet floors and wooden staircases.

## TECHNICAL DATA

Density (g/cm³):	0,90 - 0,92
Gloss Level:	Satin
Gloss level at 60°:	Semi gloss: ± 15%
Solids Content in weight:	52 - 54 %
Solids content in volume:	43 - 45 %

## DRY TIMES BY 20° C/RH 50%

Touch dry:	1,5 hours
Dry to recoat:	24 hours
Fully cured:	1 week

## RECOMMENDED WET FILM THICKNESS

100 µm

## RECOMMENDED DRY FILM THICKNESS

40 µm

## THEORETICAL CONSUMPTION

± 10 m²/l per coat

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

New parquet floors or parquet floors rub down until bare wood: dedust thoroughly, impregnate with FassiForce and let dry for minimum one night. After this, rub down lightly. Remark: replace FassiForce with diluted Duritane Gloss if the wood is colored too strongly. Old parquet floors already treated with wax: first remove the wax layer thoroughly (scrape). Use cleaning cloths soaked with white spirit. After this, apply one coat FassiForce. The FassiForce layer should be completely dry the next day. If this is not the case, it is an indication that the old wax layer was not removed enough. Clean the floor again as described above.

Remark: use sufficient cleaning cloths to remove the wax layer in order to avoid that the removed wax is applied on other parts of the floor.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

## APPLICATION & THINNING: BRUSH

If necessary dilute with maximum 5% volume white spirit or Thinner 22.

## APPLICATION & THINNING: ROLLER

If necessary dilute with maximum 5% volume white spirit or Thinner 22. Use a fine roller.

## APPLICATION & THINNING: AIRLESS SPRAY

Not recommended.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not recommended.

## CLEANING OF EQUIPMENT / SPILLS

White spirit or Thinner 22.

## REMARKS

Mix Plasti-Parket during application in order to make sure that the product will stay homogeneous.

Apply minimum 2 coats of Plasti-Parket.

## SAFETY DATA

VOC level:	445 g/l
VOC readymix:	466 g/l
VOC category:	A/i
VOC limit:	500 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 04/07/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)