

Quality Paints since 1845
MATHYS[®]



PLASTI-PARKET

Parquet floor protection

- Simple to use
- Air-drying
- Excellent resistance against abrasion
- Makes maintenance easier
- Suitable for spot repairs



PLASTI-PARKET

POPIS PRODUKTU (DLHÝ)

Solvent-based varnish based on a modified polyurethane alkyd binder.

ODPORÚČANÉ POUŽITIE

Treatment and protection of parquet floors and wooden staircases.

TECHNICAL DATA

Hustota (g/cm ³):	0,90 - 0,92
Úroveň lesku:	Satin
Úroveň lesku pri 60°:	Semi gloss: ± 15%
Obsah pevných látok v hmotnosti:	52 - 54 %
Obsah pevných látok v objeme:	43 - 45 %

DRY TIMES BY 20

Na dotyk suché:	1,5 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdnuté:	1 week

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

40 µm

TEORETICKÁ SPOTREBA

± 10 m²/l per coat

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

New parquet floors or parquet floors rub down until bare wood: dedust thoroughly, impregnate with FassiForce and let dry for minimum one night. After this, rub down lightly. Remark: replace FassiForce with diluted Duritane Gloss if the wood is colored too strongly. Old parquet floors already treated with wax: first remove the wax layer thoroughly (scrape). Use cleaning cloths soaked with white spirit. After this, apply one coat FassiForce. The FassiForce layer should be completely dry the next day. If this is not the case, it is an indication that the old wax layer was not removed enough. Clean the floor again as described above.

Remark: use sufficient cleaning cloths to remove the wax layer in order to avoid that the removed wax is applied on other parts of the floor.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

If necessary dilute with maximum 5% volume white spirit or Thinner 22.

APLIKÁCIA A RIEDENIE: VALEC

If necessary dilute with maximum 5% volume white spirit or Thinner 22. Use a fine roller.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Not recommended.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not recommended.

ČISTENIE ZARIADENIA / POSTRIEKANIE

White spirit or Thinner 22.

POZNÁMKY

Mix Plasti-Parket during application in order to make sure that the product will stay homogeneous.

Apply minimum 2 coats of Plasti-Parket.

DATA SAFETY DATA

Úroveň VOC:	445 g/l
VOC readymix:	466 g/l
Kategória VOC:	A/i
Limit VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu