



PLASTOPAN SUPER N

Solvent-based synthetic filler

- Quick hardening
- Excellent filling
- Contains no water soluble substances
- absorbs very little of the applied paint

PLASTOPAN SUPER N

BESKRIVELSE

Solvent-based synthetic filler based on linseed oil alkyd resin.

ANBEFALET BRUG

Smoothing out uneven areas in indoor and outdoor woodwork that have to be recoated with oil based or synthetic paints.

TEKNISK DATA

Tæthed:	± 2,4
Glansgrad:	Mat
Faststofindhold i vægt:	± 87 %
Tørstofindhold i volumen:	± 70 %

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	1 hour
Genbehandlingstør:	24 hours
Fuldt hærdet:	1 week

ANBEFALET VÅDFILMTYKKELSE

± 2 mm

ANBEFALET TØRFILMTYKKELSE

± 1,4 mm

TEORETISK FORBRUG

1 - 5 kg/m²

PRAKTISK FORBRUG

Depends on several factors such as porosity and roughness of the substrate and material losses during application (see DIN 53220).

FORBEHANDLING AF OVERFLADEN

Clean the substrate thoroughly, remove old weather-stained paint that is adhering poorly. Apply a thin layer of Fassiprim (diluted with ± 10% volume white spirit) on surfaces before filling them.

First treat substrates that are powdering or chalking with Fixonal. After filling and sanding, apply a primer coat of Fassiprim on all the surfaces; if matt finished portions are still visible after the primer dries, re-apply the primer to obtain a uniform appearance.

BRUGSANVISNING

Apply in a dry and well-ventilated environment.

ANVENDELSESBETINGELSER

Apply in a dry and well ventilated environment.

RENGØRING AF Udstyr/SPILD

White spirit

BEMÆRKNINGER

Apply thin layers of Plastopan Super N.

SIKKERHEDSDATA

VOC-niveau:	390 g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the packaging.

HOLDBARHED

Minimum of 2 years from date of production, if stored in the unopened, original packaging in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 07/06/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu