

Quality Paints since 1845
MATHYS[®]



PORISOL[®]

Pore-filler

- Fixing
- Isolating
- Nearly odorless
- Can be recoated with water dispersed and most synthetic paints

BESKRIVELSE

Waterborn impregnating agent.

ANBEFALET BRUG

As a pore-filler (inside): undiluted on very porous substrates (cardboard, paper, light kinds of woods), diluted on substrates with different absorption capacity (plaster, wood-fibre boards, etc.)

As a sealer (inside): undiluted on exotic wood, aniline colours and surfaces soiled with coaltar. Do not apply on substrates soiled with fume residues or soot (isolate first with Pegamat)

TEKNISK DATA

Tæthed:	1,03 - 1,06
Glansgrad:	Blank
Faststofindhold i vægt:	50 - 52 %
Tørstofindhold i volumen:	48 - 50 %

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	30 minutes
Genbehandlingstør:	1 hour

ANBEFALET VÅDFILMTYKKELSE

100 µm

ANBEFALET TØRFILMTYKKELSE

48 µm

TEORETISK FORBRUG

3 - 10 m²/l per coat

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

The surfaces to be treated must be sound and dry. Remove non adhering parts (by scraping and rubbing), dust off carefully and degrease, if necessary.

PÅFØRING OG FORTYNDING: PENSEL

If necessary dilute with water.

PÅFØRING OG FORTYNDING: RULLE

If necessary dilute with water.

RENGØRING AF Udstyr/SPILD

Water.

BEMÆRKNINGER

When used as an impregnating agent, dilute 1/1 with water on substrates soiled with fume residue or soot, use Pegamat instead of Porisol.

SIKKERHEDSDATA

VOC-niveau:	0 g/l
VOC-færdigblanding:	0 g/l
VOC-kategori:	A/g
VOC-grænse:	30 g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 09/12/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu