

Quality Paints since 1845
MATHYS[®]



VERNAC SATIN

Acrylic varnish

- Alkaliresistant
- Excellent flexibility
- High weather resistance
- Transparent
- Completely colourless

VERNAC SATIN

DESCRIPTION

Solvent based acrylic varnish.

RECOMMENDED USE

Protection of non-ferrous metals. Renovation of transparent skylights (except for polycarbonate). Do not apply Vernac Satin as floor varnish or on places that are subject to mechanical pressure.

TECHNICAL DATA

Density (g/cm ³):	0,99 - 1,01
Gloss Level:	Satin
Gloss level at 60°:	Satin gloss: ± 30%
Solids Content in weight:	49 - 51 %
Solids content in volume:	40 - 43 %

DRY TIMES BY 20° C/RH 50%

Touch dry:	1 hour
Dry to handle:	1,5 hours
Dry to recoat:	4 hours
Fully cured:	1 day

RECOMMENDED WET FILM THICKNESS

100 µm

RECOMMENDED DRY FILM THICKNESS

42 µm

THEORETICAL CONSUMPTION

10 - 15 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

The substrates must be completely dry and clean. On metals, it is necessary to remove old varnish layers (with Rapid Super, for instance) and oxidation traces (with a polish, for instance). Clean afterwards with a cloth soaked in Thinner 22.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Minimum 5°C, maximum temperature 35°C and maximum relative humidity 80 %.
No condensation during drying.
At low temperature and / or high relative humidity extend these times. The temperature of the substrate must be 3°C above the dew point.

APPLICATION & THINNING: BRUSH

Any type.

APPLICATION & THINNING: ROLLER

Mohair paint roller or short haired roller.

CLEANING OF EQUIPMENT / SPILLS

Thinner 22.

REMARKS

- 2 - 3 coats for outside works.
- 1 - 2 coats for inside works

SAFETY DATA

VOC level:	499 g/l
VOC readymix:	400 g/l
VOC category:	A/i
VOC limit:	500 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 23/10/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu